

# Product Data Sheet

# Pad Printing Ink

**SunChemical®**  
Coates Screen Inks

# TP 266

## Solvent Based Pad Printing Ink Range, 1-Component

### APPLICATION

Pad printing inks for printing of thermoplastics such as PMMA ("acrylic glass"), rigid and plasticized PVC as well as polystyrene (PS) and polystyrene co-polymers. This ink range is especially suitable for plastics with a high plasticizer content (erasers, plasticized PVC).

### PROPERTIES

- Ink range TP 266 is a solvent based 1-component pad printing ink series.
- This ink range shows a good and reliable printability
- TP 266 inks are physically quick drying inks and result in a matt to semi-gloss finish.
- TP 266 ink range is suitable for outdoor applications.
- Note: As thermoplastic injection moulds are sensitive to tension cracks pre-tests are absolutely essential for such printing applications.

### COLOUR SHADES - OVERVIEW

- Mixing System: C-MIX 2000 12 colour shades for mixing of RAL, PMS and HKS colours.
- Opaque: Standard Colour shades with medium to good opacity.
- Special colour shades are available upon request.
- More information about available colour shades in the detailed tables in section Colour Shades.

### CHOICE OF PIGMENTS AND LIGHT FASTNESS

Colour shades of TP 266 ink range contain pigments with a high light fastness. Light fastness and weather resistance will reduce if thinner layers are applied or if base colours are mixed with a high ratio of white or varnish.

Applied on suitable substrates pad printing inks TP 266 are suitable for outdoor applications.

### ADJUSTMENT FOR PAD PRINTING

- Pad printing inks TP 266 are not supplied in a ready-to-print adjustment.
- The ink is adjusted for printing by addition of thinner or retarder (stir with mixer, agitator).
- Prior to printing, the inks should be stirred well to obtain a homogeneous dispersion of all ingredients.

### THINNERS / RETARDERS

Depending on local conditions, the ink is adjusted for printing by addition of 15 to 35 % by weight thinner or retarder.

**Generally, the thinner suitable for TP 266 is [Additive A!](#)**

The additional products listed below should only be used if the required printing quality/ink transfer cannot be achieved using Additive A (e.g. drying too slow or too fast).

For adjustment of pad inks TP 266, the following products are available:

<b>Thinner:</b>	<input type="radio"/> Additive C	Extremely quick thinner, good solving power
	<input type="radio"/> VD 40	Quick, very strong solving power
	<input type="radio"/> Additive B	Quick thinner, good solving power
	<input checked="" type="radio"/> <b>Additive A</b>	<b>Standard thinner</b>
	<input type="radio"/> Additive U	Standard thinner, free of cyclohexanone
	<input type="radio"/> VD 60	Slow thinner
<b>Retarder:</b>	<input type="radio"/> TPD	Very slow retarder
	■= Preferred    ○= If required	
<b>Note:</b>	<b>For printing with thick and thin steel clichés sensitive to corrosion</b>	
	<input type="radio"/> Additive A/00	Standard thinner with anti-corrosion additive
	<input type="radio"/> Additive B/00	Standard thinner with anti-corrosion additive

Depending on printing conditions, the products listed above can be mixed into the inks individually or as mixtures. Please note that depending on evaporation rate of the thinner/retarder used drying times may be longer.

Thinner/retarder should be mixed into the ink thoroughly using a mixer or agitator. In addition, inks should be stirred well prior to each processing to obtain a homogeneous dispersion of all ingredients.

#### ADDITIONAL AUXILIARY AGENTS

Application	Product	Addition in % by weight	Additional Information
Antistatic paste	LAB-N 111420	Max. 10%	Possibly slightly reduced gloss
Retarder paste	LAB-N 111420/VP	Max. 10%	Possibly slightly reduced gloss
Viscosity increase	Thickening powder	Max. 3%	Stir with mixer
Flow agent	VM 1	1 - 5%	Do not overdose!

#### OVERPRINTING

Generally, it is not necessary to overprint TP 266 inks with varnish. Basically overprinting to achieve an enhanced protection of ink layers is possible with TP 266/E50.

#### BRONZE COLOURS, MIXING OF BRONZE INKS

Bronze colours may be available upon request.

Printers can mix bronzes themselves using bronze pastes B 75, B 76, B 77 and B 79 as well as bronze powder B 78-POWDER. For examples of colour shades please refer to our Bronze Colour Card.

These “B” bronze pastes and “B” bronze powder are mixed with varnish TP 266/E50 prior to processing.

Mixing ratios in parts by weight:

Gold bronze paste/powder	to	TP 266/E50	=	1 : 3 - 4
Silver bronze paste	to	TP 266/E50	=	1 : 4 - 6

Bronzes B 75 to B 79 are prone to oxidation (Exception B 78-POWDER). Therefore they should be overprinted, e.g. with TP 266/E50. B-bronzes are not recommended for long-term outdoor applications.

B 78-POWDER does not tend to oxidation. The pale copper shade will not darken with time. Colour of inks mixed with B 78-POWDER is similar to colour 78/AB as shown on our “bronze colour card”.

Note: When overprinting bronze colours with varnish or other colour shades it is essential to carry out pre-tests to check intermediate adhesion of the ink layers (fingernail test, tape test). Possibly mixing ratio needs to be changed to a higher varnish ratio (between 10 – 30%).

**DRYING**

TP 266 pad printing inks dry physically, i.e. by evaporation of solvents.

Drying times below are only approximate as drying properties depend on various factors:

- Type and amount of thinners/retarders used.
- Thickness of printed ink layer (single print, multiple prints)
- Drying temperature.

Drying time is approx. 2 minutes at room temperature (20 – 25°). Drying time with heat application (e.g. hot air fan) and air circulation is about 20 - 40 seconds.

Complete drying may take up to 15 minutes, also depending on the substrate.

**Resistance Tests**

Resistances should not be checked before the prints are completely dry.

**CLICHÉ**

All commercial types of clichés (polymer, thin and thick steel, ceramic) are suitable for processing TP 266 inks.

Note: Standard shades 17, 50 and 51 cannot be used for closed ink systems with a magnet holder as they contain pigments with iron oxide content.

**CLEANING**

Clichés, ink pots and tools can be cleaned with our universal cleaning agents URS, URS 3 or thinner VD 40.

**PACK SIZE**

Pad printing inks TP 266 are delivered in 1 litre containers. Other pack sizes are available upon request.

**SHELF LIFE**

In closed original containers, TP 266 inks generally have a shelf life of 5 years from date of production.

For exact date of expiry, please refer to the label.

**SAFETY DATA SHEETS**

Read safety data sheet prior to processing

Safety data sheets comply with Regulation (EC) No. 1907/2006 (REACH), Appendix II.

**CLASSIFICATION AND LABELLING**

Hazard classification and labelling comply with Regulation (EC) No. 1272/2008 (CLP/GHS).

**CONFORMITY**

Coates Screen Inks GmbH does not use any of the substances or mixtures for the production of printing inks, which are banned according to the EUPIA (European Association of the Printing Inks Industry) exclusion policy.

Further compliance confirmations are available upon request.

**ADDITIONAL INFORMATION ABOUT OUR PRODUCTS**

Product data sheets: Auxiliary Agents for Pad Printing HM

Brochures: Pad Printing Inks

Internet: Various technical articles are available for download on [www.coates.de](http://www.coates.de), section "SN-Online"

**FOR COLOUR RANGES, PLEASE REFER TO NEXT PAGE.**

**COLOUR SHADES**

<b>C-MIX 2000 BASE COLOUR SHADES</b>					
<b>Mixing system for matching of PMS, HKS, RAL colours (on white substrates)</b> Start formulations available in data base „Formula Management C-MIX 2000“ <b>According to colour card C-MIX 2000</b>					
primrose	TP 266/Y30	red	TP 266/R50	green	TP 266/G50
golden yellow	TP 266/Y50	magenta	TP 266/M50	black	TP 266/N50
orange	TP 266/O50	violet	TP 266/V50	white	TP 266/W50
scarlet	TP 266/R20	blue	TP 266/B50	varnish	TP 266/E50
<b>STANDARD Colour Range (medium opacity)</b>					
<b>According to colour card STANDARD 1 for pad printing inks or TP 247/ TP 249...</b> Availability of further standard shades upon request					
white	TP 266/60-NT	black	TP 266/65-NT		
<b>STANDARD Colour Range HD (high opacity)</b>					
<b>According to colour card STANDARD HD for Pad printing inks</b>					
Not available					
<b>SPECIAL PRODUCTS: Special Colour Shades, Varnishes, Pastes</b>					
Information about availability upon request					
Upon request					
<b>4 COLOUR PROCESS INKS (CMYK)</b>					
<b>According to colour card STANDARD 1 for pad printing inks TP 247/ TP 249...</b> Information about availability upon request					
Upon request					
<b>AB – BRONZE INKS and MG – METAL GLOSS INKS</b>					
According to Bronze Colour Card					
AB Bronze Inks			MG Metal Gloss Inks		
Upon request			Not available		

Matching of PMS, RAL, NCS colours and special shades upon request.

*The statements in our product and safety data sheets are based on our present experiences, however they are no assurance of product properties and do not justify a contractual legal relationship. We provide these details to inform customers about our products and their possible applications. However, on account of various factors influencing processing of our products it is absolutely essential to carry out printing trials under local production conditions. Choice of individual ink types and their suitability for the intended application is the sole and entire responsibility of the user. We do not assume any liability for any problems of technical or process-related nature. Any liability shall be limited to the value of the goods delivered by us and processed by the user.*

*All former product data sheets are no longer valid.*

April 2020 - Version B2

**Coates Screen Inks GmbH**  
 Wiederholdplatz 1 90451 Nürnberg  
 Tel.: 0911 6422 0 Fax: 0911 6422 200  
<http://www.coates.de>